

Cromapur Natura

Matlacquer 452270

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Product

Cromapur Natura 452270

Productdescription

Transparent 2-component lacquer for both ground lacquer and top coat with a beautiful natural appearance.

Field of application

High quality acrylic paint for the carpentry and furniture industry

Technical data

| | |
|--------------------|---------------------------------------------------------------------------------|
| Colour | Natural transparent. |
| Gloss | 5-10 very matt |
| Mixing ratio | 100 part Cromapur 452270 + 25 % Hardener 46000 by weight |
| Thinner | 30% SO 660110 on the mix |
| Delivery viscosity | Ca. 50 sec. |
| Spray viscosity | 16-21 sec. |
| Potlife | Ca.8 hour at 20°C |
| Solid contents | ca. 27% sec. |
| Storage stability | Stored in original unopened packaging for 12 months in a cool, frost-free place |

application

| | |
|-------------------------------|-------------------------------------------------------------------|
| Application method | Spray |
| Layers | 1-2 layers |
| Yield per layer | 80-100 gr/m |
| Max. Yield | 120 gr/m |
| Optimal temp. working space | 16-18 C ⁰ |
| Optimal humidity | 60% |
| Material temperature | 16-20 C ⁰ |
| Cleaning Thinner | SO 602020 |
| Pre-treatment of wood | P 120 |
| Suitable on bleached wood | no |
| UV resistance | Yes |
| Optimal moisture content wood | 12-14 %. |
| Drying times | 10 min. dust dry at 20 C 1 hour sand able 16 hour stackable |

Disposal

Treat waste from paints or oil as chemical waste.

dispose of as chemical waste.

Package

5 of 10 or 25 Kg cans

Safety, Standards and durability

UN Code 1263, paint, 3, VG II, (D/E) , GGVS / ADR

Info Safety data sheet

