

## Product information

# BASIC

## 2K water based nature coat

377374.3

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.



Plantag Coatings Groep

Delta 32, 6825 MS Arnhem

T +31 (0) 26 388 21 02

F +31 (0) 26 364 41 51

Email: [info@plantag.nl](mailto:info@plantag.nl)

Website: [www.plantag.nl](http://www.plantag.nl)

## Product

Basic 2K water based nature coat 377374.3.

## Product description

BASIC 2K nature effect coat is an environmentally friendly alternative to the conventional paint systems with less than 3% solvent. This lacquer gives the wood a natural untreated appearance with excellent protection.

## Field of application

As Base and Topcoat for high quality finishing in the carpentry and furniture industry.

## Technical data

Color	Transparent
Gloss	0-5 Matt
Mixing ratio	100 part BASIC 377374.3 + 10 parts Hardener 75109.6 weight
Thinner	5 a 10 % water
Delivery viscosity	Ca. 25-30 sec.
Spray viscosity	25-30 sec.
Potlife	Ca. 4 hour at 20 °C
Solid contents	Ca. 30 %
Storage stability	Stored in original unopened packaging for 6 months in a cool, frost-free place. Stir before use. Avoid contact with iron, copper, zinc and aluminum or other similar

# BASIC

## 2K water based nature coat 377374.3

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

### Application

Application method	Spray or roll
Layers	2 layers
Yield per layer	100-120 gr/ m <sup>2</sup>
Max. Yield	150 gr/ m <sup>2</sup>
Optimal temp. working space	16-18 °C
Optimal humidity	60 %
Material temperature	16-20 °C
Cleaning Thinner	Water
Pre-treatment of wood	P 120
Suitable on bleached wood	Not applicable
UV resistance	Yes
Optimal moisture content wood	12-14 %
Drying times	30 min. dust dry at 20 °C. 2 hours limited sanded. 4 hours sanded. 16 hour stackable. Forced drying will reduce the drying time.

### Disposal

Treat waste from paints or oil as chemical waste dispose of as chemical waste.

### Package

Available in 5 or 25 Kg cans

### Safety, Standards and durability

UN Code: NO ADR.

Info: Safety data sheet.

