

Product information

Cromapur 45053

Color lacquer

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.



Delta 32, 6825 MS Arnhem
T +31 (0) 26 388 21 02
F +31 (0) 26 364 41 51
Email: info@plantag.nl
Website: www.plantag.nl

Product


Cromapur 45053 2K Polyurethane lacquer, is a very high-quality, silk matt multi-layer lacquer with perfect light resistance, very high mechanical and chemical resistance.

Field of application

Cromapur colored lacquer 45053, Available in a large number of colors, including the Ral / NCS. Other colors available on request. High quality acrylic lacquer can be used for various application areas, including the carpentry, furniture and kitchen industry.

Technical data

Gloss	Silk Matt
Color	RAL, NCS
Gloss	25-30
Mixing ratio	100 part Cromapur 45053 + 10 parts Hardener 46000 by weight
Thinner	Max 10 % AC 660110
Delivery viscosity	Ca. 30-50 sec.
Spray viscosity	25-35 sec.
Potlife	Ca. 24 hour at 20°C
Solid contents	ca. 26-50%
Storage stability	Stored in original unopened packaging for 12 months in a cool, frost-free place



Product information

Cromapur 45053

Color lacquer

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information

PCG

Plantag Coatings Groep

Delta 32, 6825 MS Arnhem

T +31 (0) 26 388 21 02

F +31 (0) 26 364 41 51

Email: info@plantag.nl

Website: www.plantag.nl

application

Application method	Spray
Layers	1-2 layers
Yield per layer	100-120 gr/m
Max. Yield	120 gr/m
Optimal temp. working space	16-18 C°
Optimal humidity	60%
Material temperature	16-20 C°
Cleaning Thinner	SO 602020
Pre-treatment of wood	P 120
Suitable on bleached wood	Does not applicable
UV resistance	Good
Optimal moisture content wood	12-14 %.
Drying times	10 min. dust dry at 20 C 2 hours sandable 16 hour stackable

Disposal

Treat waste from paints or oil as chemical waste.
dispose of as chemical waste.

Package

5 of 10 or 25 Kg cans

Safety, Standards and durability

Complies with the following standards DIN 688611B, EN71 Part 3, DIN 53160
UN Code 1263, paint, 3, VG II, (D/E) , GGVS / ADR. Info Safety data sheet

