

Product information

Cromapur

Natura 452270

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.



Delta 32, 6825 MS Arnhem
T +31 (0) 26 388 21 02
F +31 (0) 26 364 41 51
Email: info@plantag.nl
Website: www.plantag.nl

Product

Cromapur Natura 452270 Polyurethane transparent 2K acrylic lacquer, with a natural matt appearance. This Lacquer is fast drying and easy to sand and can be used as both ground and topcoat.

Product description

Cromapur Natura, can be used perfectly as finishing, whereby the natural appearance of the wood remains intact. This lacquer gives a nice note of the wood and meets the high quality requirements that may be set for durability.

Field of application

Universally applicable high quality 2k lacquer.

Technical data

Gloss	5-10
Colour	Natural transparent.
Mixing ratio	100 part Cromapur AC 452270 + 25 % Hardener 46000.
Thinner	30 part SO 660110/ SO 660668
Delivery viscosity	Ca. 50 sec.
Spray viscosity	16-21 sec.
Potlife	Ca. 8 hour at 20°C
Solid contents	Ca. 19 % sec.
Storage stability	Stored in original unopened packaging for 12 months in a cool, frost-free place



Product information

Cromapur

Natura 452270

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

PCG

Plantag Coatings Groep

Delta 32, 6825 MS Arnhem

T +31 (0) 26 388 21 02

F +31 (0) 26 364 41 51

Email: info@plantag.nl

Website: www.plantag.nl

Application

Application method	Spray
Layers	More layers
Yield per layer	80 - 100 gr/m ²
Max. Yield	120 gr/ m ²
Optimal temp. working space	16 - 18°C
Optimal humidity	60 %
Material temperature	16 - 20°C ⁰
Cleaning Thinner	SO 602020
Pre-treatment of wood	P 320
Suitable on bleached wood	No
UV resistance	Yes
Optimal moisture content wood	12 - 14 %
Drying times	10 min. dust dry 30 min. sand able 16 hour stackable Forced drying will reduce the drying time.

Disposal

Dispose of paint waste as chemical waste in such a way.

Package

Available in 25 Kg.

Safety, Standards and durability

Standards: DIN 68861.1B, DIN 4102-B1, DIN 53160 en EN 71- 3.

UN Code 1263, paint, 3, VG II, (D/E), GGVS / ADR

Info Safety data sheet

