

# ECO Nature oil

## OL 178293.7

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem  
T +31 (0) 26 388 21 02  
F +31 (0) 26 364 41 51  
Email: [info@plantag.nl](mailto:info@plantag.nl)  
Website: [www.plantag.nl](http://www.plantag.nl)

## Product

ECO Nature oil OL 78293.7

## Productdescription

Eco natural oil is the environmentally friendly alternative to the finishing of wood and furniture. Eco natural oil, based on natural resources, has excellent impregnating properties and water resistance. It gives a very nice note of the wood. The Eco natural oil can be used as either 1k or 2k

## Field of application

Wood and furniture industry

## Technical data

Gloss	Mat
Color	Available in various trendy colors.
Mixing ratio	As use at 2K ad max 5% 01786 hardener
Verdunning	n.v.t.
Delivery viscosity	45-55 sec. Din 53211/4mm
Potlife	Not applicable
Solid parts	ca. 87 %
Storage stability	In the original unopened package, frost-free, 6 months

# VOC-Vrije Olie

## OL 178293.7

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem  
T +31 (0) 26 388 21 02  
F +31 (0) 26 364 41 51  
Email: [info@plantag.nl](mailto:info@plantag.nl)  
Website: [www.plantag.nl](http://www.plantag.nl)

### application

Application method	By brush roller or with cloths
Layers	1-2
Yield per layer	30-40 gr/m
Optimal temp. working space	16-18 C <sup>0</sup>
Optimal humidity	60%
Material temperature	16-20 C <sup>0</sup>
Cleaning Thinner	not applicable
Pretreatment of wood	P 120
Suitable on bleached wood	no
UV resistance	Limited
Optimal moisture content wood	12-14 %.
Drying times	Preferably 1 night at 20 <sup>0</sup> C. For the full load we advise to let the oil dry for 5 days

### Disposal

Treat waste from paints as chemical waste.  
dispose of as chemical waste.

### Package

1, 5 of 10 Kg cans

### Safety, Standards and durability

The used cloths with the oil can self-ignite due to heating. Hang the used cloths in a well-ventilated area and dispose of them in the normal waste after 48 hours. The used cloths can also be immersed in a barrel with water.

UN Code 1263, paint, 3, VG II, (D/E) , GGVS / ADR /Info

Safety data sheet