

# Water stain

## BP 710xxxx

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem  
T +31 (0) 26 388 21 02  
F +31 (0) 26 364 41 51  
Email: [info@plantag.nl](mailto:info@plantag.nl)  
Website: [www.plantag.nl](http://www.plantag.nl)

## Product

Water stain BP 810xxxx

## Productdescription

Water based stain for all kind of Wood in various colors

## Field of application

Carpentry and furniture industry.

## Technical data

|                    |   |
|--------------------|---|
| Colour             | Various   |
| Gloss              | Does not apply  |
| Mixing ratio       | Does not apply  |
| Thinner            | SO 75123.1 or SO 75123.2  |
| Delivery viscosity | 12-14 sec   |
| Spray viscosity    | 12-14 sec   |
| Potlife            | Does not apply  |
| Solid contents     | ca. 10 %  |
| Storage stability  | Stored in original unopened packaging for 12 months in a cool, frost-free place |

# Nitro stain

## BP 810xxxx

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem  
T +31 (0) 26 388 21 02  
F +31 (0) 26 364 41 51  
Email: [info@plantag.nl](mailto:info@plantag.nl)  
Website: [www.plantag.nl](http://www.plantag.nl)

### application

|                               |  |
|-------------------------------|--|
| Application method            | By brush, spray, roller or with cloths |
| Layers                        | 1                                      |
| Yield per layer               | 20-30 gr/m                             |
| Optimal temp. working space   | 16-18 C°                               |
| Optimal humidity              | 60%                                    |
| Material temperature          | 16-20 C°                               |
| Cleaning Thinner              | SO 602020                              |
| Pre-treatment of wood         | P 120                                  |
| Suitable on bleached wood     | no                                     |
| UV resistance                 | Limited                                |
| Optimal moisture content wood | 12-14 %.                               |
| Drying times                  | 15 min at 20 C                         |

### Disposal

dispose of as chemical waste.

### Package

5 of 10 or 25 Kg cans

### Safety, Standards and durability

UN Code 1263, paint, 3, VG II, (D/E) , GGVS / ADR

Info                      Safety data sheet

