

## Product information

# Patina ESD

872067

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.



Delta 32, 6825 MS Arnhem  
T +31 (0) 26 388 21 02  
F +31 (0) 26 364 41 51  
Email: [info@plantag.nl](mailto:info@plantag.nl)  
Website: [www.plantag.nl](http://www.plantag.nl)

## Product

Patina is a quick-drying color solution in solvent and water to create special effects in wood.

## Product description


Patina gives a characteristic appearance to the wood. For creating beautiful wood grain notes and / or shadow effects. Available in various colors. After applying and drying, the Patina must be coated with a transparent lacquer.

## Field of application

For the wood, furniture and carpentry industry.

## Technical data

Color	Black
Gloss	not applicable
Mixing ratio	ready for use
Thinner	Water, SO 602000
Delivery viscosity	Ca. 10-12 sec.
Spray viscosity	10-12 sec.
Potlife	not applicable
Solid contents	Ca. 2,5 %
Storage stability	Stored in original unopened packaging for 6 months in a cool, frost-free place.



## Product information

# Patina ESD

872067

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

# PCG

Plantag Coatings Groep

Delta 32, 6825 MS Arnhem

T +31 (0) 26 388 21 02

F +31 (0) 26 364 41 51

Email: [info@plantag.nl](mailto:info@plantag.nl)

Website: [www.plantag.nl](http://www.plantag.nl)

## Application

Application method	spray
Layers	depends on required effect
Yield per layer	depends on required effect
Optimal temp. working space	16-18 °C (do not use under 15 °C )
Optimal humidity	60 %
Material temperature	16-20 °C
Cleaning Thinner	SO 602000
Pre-treatment of wood	P 320
Suitable on bleached wood	Not applicable
UV resistance	-
Optimal moisture content wood	12-14 %
Drying times	10 min. at 20 °C Forced drying will reduce the drying time.

## Disposal

Treat waste from paints or oil as chemical waste dispose of as chemical waste.

## Package

Available in 5, 10 or 25 Kg cans

## Safety, Standards and durability

UN code 1263, Paint, 3, VG II, (D/E), GGVS/ADR.

Info: Safety data sheet.

