

Placrylat

Aufheller 367771.1

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem
T +31 (0) 26 388 21 02
F +31 (0) 26 364 41 51
Email: info@plantag.nl
Website: www.plantag.nl

Product

Placrylat Aufheller 367771. High quality, 2 component base coat.

Product description


Placrylat Aufheller 367771.1 is a quick-drying and easily sandable primer based on acrylic resins. This lacquer has an uplifting effect.

Field of application

High quality acrylic-based lacquer for the wood and furniture industry.

Technical data

Gloss	Does not apply
Color	Natural Transparent
Mixing ratio	100 part AC 367771.1 + 7 parts VC 562376.
Thinner	Max. 10 % AC SO 660110/ SO 660668
Delivery viscosity	19-21 sec.
Spray viscosity	19-21 sec.
Potlife	Ca. 8 hour at 20°C
Solid contents	Ca. 23 %
Storage stability	Stored in original unopened packaging for 12 months in a cool, frost-free place.



This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

application

Application method	Spray
Layers	1-2 layers
Yield per layer	80-100 gr/m ²
Max. Yield	120 gr/m ²
Optimal temp. working space	16-18 °C
Optimal humidity	60 %
Material temperature	16-20 °C
Cleaning Thinner	SO 602020
Pre-treatment of wood	P 120
Suitable on bleached wood	No
UV resistance	Good
Optimal moisture content wood	12-14 %
Drying times	15 min. dust dry. 45 min. sand with care. 60 min. be sanded and painted. Forced drying will reduce the drying time.

Disposal

Treat waste from paints or oil as Chemical waste.

Package

Available in 25 or 200 Kg cans.

Safety, Standards and durability

UN Code 1263, paint, 3, VG II, (D/E), GGVS / ADR
Info: Safety data sheet.

