

Product information

Placrylat

Base Coat Speed 366682

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.



Delta 32, 6825 MS Arnhem
T +31 (0) 26 388 21 02
F +31 (0) 26 364 41 51
Email: info@plantag.nl
Website: www.plantag.nl

Product

Placrylat Base Coat Speed transparent 2K lacquer

Product description

Placrylat Base Coat Speed is a transparent, very clear, fast drying and highly sandable acrylic-based primer.

Field of application

For the furniture, wood and kitchen industry.

Technical data

Gloss	no applicable
Color	Natural transparent.
Mixing ratio	100 parts 366682 + 12 parts Hardener VC 562376 by weight.
Thinner	10% SO 660110
Delivery viscosity	30-32 sec.
Spray viscosity	17-28 sec.
Potlife	Ca. 6 hour at 20°C
Solid contents	Ca. 26.5 %
Storage stability	Stored in original unopened packaging for 12 months in a cool, frost-free place



Product information

Plaquadur

Base Coat Speed 366682

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

PCG

Plantag Coatings Groep

Delta 32, 6825 MS Arnhem

T +31 (0) 26 388 21 02

F +31 (0) 26 364 41 51

Email: info@plantag.nl

Website: www.plantag.nl

Application

Application method	Spray
Layers	1 or multiple layers
Yield per layer	100-150 gr/m ²
Optimal temp. working space	16 - 18°C
Optimal humidity	60 %
Material temperature	16 - 20°C ⁰
Cleaning Thinner	SO 602020
Pre-treatment of wood	P 120, sanding base coat P 320
Suitable on bleached wood	No
UV resistance	yes
Optimal moisture content wood	12 - 14 %
Drying times	10 min. dust dry 180 min. sand able

Forced drying will reduce the drying time.

Disposal

Dispose of paint waste as chemical waste in such a way.

Package

Available in 25 Kg.

Safety, Standards and durability

Standards: DIN 53160 en EN 71- 3

UN Code 1263, paint, 3, VG III, (D/E), GGVS / ADR

Info Safety data sheet

