

Product information

Placrylat

Nature effect 373491.5

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Product

Placrylat Nature Effect lacquer 373491.5 is a transparent 2-component lacquer.

Product description

Placrylat Nature Effect 373491.5 is a transparent 2-component lacquer for top coat with a beautiful natural appearance and ultra matt, with a natural look. the system must be built with a placrylat base coat.

Field of application

High quality transparent 2-component lacquer for the carpentry and furniture industry.

Technical data

Color	Natural transparent
Gloss	0-5 ultra matt
Mixing ratio	100 part AC 373491.5 + 12 parts Hardener VC 562376
Thinner	If necessary 10% AC thinner SO 660110/ SO 660668
Delivery viscosity	Ca. 22-24 sec.
Spray viscosity	18-24 sec.
Potlife	Ca. 8 hour at 20°C
Solid contents	Ca. 23 % sec.
Storage stability	Stored in original unopened packaging for 12 months in a cool, frost-free place.



Product information

Placrylat

Nature effect 373491.5

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

PCG

Plantag Coatings Groep

Delta 32, 6825 MS Arnhem

T +31 (0) 26 388 21 02

F +31 (0) 26 364 41 51

Email: info@plantag.nl

Website: www.plantag.nl

Application

Application method	Spray
Layers	1 or 2 layer
Yield per layer	80-100 gr/ m ²
Max. Yield	120 gr/ m ²
Optimal temp. working space	16-18 °C
Optimal humidity	60 %
Material temperature	16-20 °C
Cleaning Thinner	SO 602020
Pre-treatment of wood	P 320
Suitable on bleached wood	No
UV resistance	Yes
Optimal moisture content wood	12 - 14 %.
Drying times	15 min. dust dry. 180 min approachable. 16 hours packable. Forced drying will reduce the drying time.

Disposal

Treat waste from paints or oil as chemical waste dispose of as chemical waste.

Package

Available in 25 or 180 Kg Cans.

Safety, Standards and durability

Complies with the following standards DIN 68861.1B.

UN Code 1263, paint, 3, VG II, (D/E), GGVS / ADR.

Info: Safety data sheet.

