

## Product information

# Placrylat

## Base Coat 369891.3

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

## Product

Placrylat Base Coat 369891.3 transparent 2K lacquer

## Product description


Placrylat Base Coat is a transparent, highly filling and highly sandable acrylic-based primer. Can be used perfectly when a closed surface or wood grain is desired.

## Field of application

For the furniture, wood and kitchen industry.

## Technical data

Gloss	no applicable
Colour	Natural transparent.
Mixing ratio	100 parts 369891.3 + 15 parts Hardener VC 562376 by weight.
Thinner	10% SO 660110
Delivery viscosity	32-34 sec.
Spray viscosity	21-30 sec.
Potlife	Ca. 8 hour at 20°C
Solid contents	Ca. 32.8 %
Storage stability	Stored in original unopened packaging for 12 months in a cool, frost-free place



## Product information

# Plaquadur

## Base Coat 369891.3

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

# PCG

Plantag Coatings Groep

Delta 32, 6825 MS Arnhem

T +31 (0) 26 388 21 02

F +31 (0) 26 364 41 51

Email: [info@plantag.nl](mailto:info@plantag.nl)

Website: [www.plantag.nl](http://www.plantag.nl)

## Application

Application method	Spray
Layers	1 layer
Yield per layer	150-250 gr/m <sup>2</sup>
Optimal temp. working space	16 - 18°C
Optimal humidity	60 %
Material temperature	16 - 20°C <sup>0</sup>
Cleaning Thinner	SO 602020
Pre-treatment of wood	P 120, sanding base coat P 320
Suitable on bleached wood	No
UV resistance	yes
Optimal moisture content wood	12 - 14 %
Drying times	15 min. dust dry 120 min. sand able

Forced drying will reduce the drying time.

## Disposal

Dispose of paint waste as chemical waste in such a way.

## Package

Available in 25 Kg.

## Safety, Standards and durability

Standards: DIN 53160 en EN 71- 3

UN Code 1263, paint, 3, VG III, (D/E), GGVS / ADR

Info Safety data sheet

