

Plantulose

Plantulose base coat NC 170380

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem
T +31 (0) 26 388 21 02
F +31 (0) 26 364 41 51
Email: info@plantag.nl
Website: www.plantag.nl

Product

Plantulose base coat NC 170380.

Product description

Plantulose base coat NC 170380 is a high-quality, easy-to-sand paint that can be used as a base coat

Field of application

High quality, excellent primer for the carpentry and furniture industry.

Technical data

Gloss	Not applicable
Color	Transparent
Mixing ratio	Not applicable
Thinner	NC SO 600239 NC SO 602020 AC SO 660110
Delivery viscosity	35-40 sec.
Spray viscosity	17-40 sec.
Potlife	Not applicable
Solid contents	Ca. 28 %
Storage stability	Stored in original unopened packaging for 12 months in a cool, frost-free place

Plantulose

Plantulose base coat NC 170380

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem
T +31 (0) 26 388 21 02
F +31 (0) 26 364 41 51
Email: info@plantag.nl
Website: www.plantag.nl

Application

Application method	Spray
Layers	1-2 layers
Yield per layer	90-120 gr/ m ²
Max. Yield	120 gr/ m ²
Optimal temp. working space	16-18 °C
Optimal humidity	60 %
Material temperature	16-20 °C
Cleaning Thinner	SO 602020
Pre-treatment of wood	P 120
Suitable on bleached wood	Not applicable
UV resistance	Limited
Optimal moisture content wood	12-14 %.
Drying times	8 min. dust dry. 30 min. limited sandable. 60 min. sandable. Forced drying will reduce the drying time.

Disposal

Treat waste from paints or oil as chemical waste, dispose of as chemical waste.

Package

Available in 30 or 200 Kg cans.

Safety, Standards and durability

UN Code: 1263, paint, 3, VG II, (D/E), GGVS / ADR.
Info: Safety data sheet

