

## Product information

# AC 161283

## Adhesive primer PE/PP

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.



Delta 32, 6825 MS Arnhem  
T +31 (0) 26 388 21 02  
F +31 (0) 26 364 41 51  
Email: [info@plantag.nl](mailto:info@plantag.nl)  
Website: [www.plantag.nl](http://www.plantag.nl)

## Product

1K Transparent Adhesive Primer for PE/PP AC 161283.

## Productdescription

Adhesive primer based on chlorinated polyolefin

## Field of application

Fast drying adhesive primer for various plastics such as PE, PP, PVC, to ensure the underground and finish. Perform a test on the substrate to be used before the start.

## Technical data

Colour	Transparent
Gloss	Does not applicable
Mixing ratio	Does not applicable
Thinner	Does not applicable
Delivery viscosity	Ca. 11 sec.
Spray viscosity	Ca. 11 sec.
Potlife	Does not applicable
Solid contents	ca. 2,5 %
Storage stability	In original unopened packaging 12 months in a cool, dry and frost-free place



## Product information

# AC 161283

## Adhesive primer PE/PP

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.



Delta 32, 6825 MS Arnhem  
T +31 (0) 26 388 21 02  
F +31 (0) 26 364 41 51  
Email: [info@plantag.nl](mailto:info@plantag.nl)  
Website: [www.plantag.nl](http://www.plantag.nl)

## application

Application method	Spray
Layers	1 layer
Yield per layer	10-30 gr/ m <sup>2</sup>
Max. Yield	30 gr/ m <sup>2</sup>
Optimal temp. working space	16-18 °C
Optimal humidity	60 %
Material temperature	16-20 °C
Cleaning Thinner	SO 602020
Pre-treatment of wood	Clean good
Suitable on bleached wood	Does not applicable
UV resistance	Does not applicable
Optimal moisture content wood	Does not applicable
Drying times	30-60 sec. dust dry at 20 °C. Forced drying will reduce the drying time.

## Disposal

Treat waste from paints or oil as chemical waste, dispose of as chemical waste.

## Package

Available in 10 kg cans.

## Safety, Standards and durability

UN Code 1263, paint, 3, VG II, (D/E) , GGVS / ADR  
Info: Safety data sheet

