

# Urethane oil

## OL 177328.1

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem  
T +31 (0) 26 388 21 02  
F +31 (0) 26 364 41 51  
Email: [info@plantag.nl](mailto:info@plantag.nl)  
Website: [www.plantag.nl](http://www.plantag.nl)

## Product

Urethane oil OL 177328.1

## Productdescription

The Urethane oil OL 177328.1 can be supplied in many beautiful trend colors and gives the wood a very nice note. Urethane Oil is very easy to process. Has excellent impregnating properties, resulting in good dirt and water resistance. For both indoor and outdoor use.

## Field of application

Carpentry and furniture industry.

## Technical data

Color	Available in various trendy colors.
Gloss	Matt
Mixing ratio	Does not applicable
Verdunning	SO 602005 or SO 602006
Delivery viscosity	14-16 sec. Din 53211/4mm
Potlife	Does not applicable
Solid parts	ca. 30 %
Storage stability	In the original unopened package, frost-free, 6 months

# Urethane oil

## OL 177328.1

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem  
T +31 (0) 26 388 21 02  
F +31 (0) 26 364 41 51  
Email: [info@plantag.nl](mailto:info@plantag.nl)  
Website: [www.plantag.nl](http://www.plantag.nl)

## application

Application method	By brush, spray, roller or with cloths
Layers	1-2
Yield per layer	20-30 gr/m
Optimal temp. working space	16-18 C <sup>0</sup>
Optimal humidity	60%
Material temperature	16-20 C <sup>0</sup>
Cleaning Thinner	not applicable
Pre-treatment of wood	P 120
Suitable on bleached wood	no
UV resistance	Limited
Optimal moisture content wood	12-14 %.
Drying times	Preferably 1 night at 20 <sup>0</sup> C. For the full load we advise to let the oil dry for 5 days

## Disposal

Treat waste from paints or oil as chemical waste.  
dispose of as chemical waste.

## Package

1, 5 of 10 Kg cans

## Safety, Standards and durability

The used cloths with the oil can self-ignite due to heating. Hang the used cloths in a well-ventilated area and dispose of them in the normal waste after 48 hours. The used cloths can also be immersed in a barrel with water.

UN Code 1263, paint, 3, VG II, (D/E) , GGVS / ADR /Info

Safety data sheet