

Product information

Variopur Primo

VT 33055-6-XXXX

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.

Delta 32, 6825 MS Arnhem
T +31 (0) 26 388 21 02
F +31 (0) 26 364 41 51
Email: info@plantag.nl
Website: www.plantag.nl

Product

Variopur Primo VT 33055-6-XXXX, high-quality, 2K polyurethane color lacquer.

Productdescription


Variopur Primo VT 33055-6-XXXX, high-quality pigmented multi-layer lacquer specially for MDF finishing. This lacquer can replace the conventional spray filler and color lacquer. This quick-drying lacquer is very easy to sand, strong fill and ring-proof. Can also be used as a topcoat on spray fillers.

Field of application

High quality acrylic color lacquer for the carpentry and furniture industry.

Technical data

Colour	RAL and NCS
Gloss	Ca. 25-30
Mixing ratio	100 parts Variopur VT 33055-6-XXX + 50 parts Hardener VT 38055
Thinner	Max. 10 % AC 660110
Delivery viscosity	Thixotropic
Spray viscosity	20-25 sec.
Potlife	Ca. 2-3 hour at 20°C
Solid contents	Ca. 64 %
Storage stability	Stored in original unopened packaging for 12 months in a cool, frost-free place



Product information

Variopur Primo

VT 33055-6-XXXX

This magazine has an advisory function. However, the user must test the application of this product against the circumstances and possibilities that apply to him. No liability or guarantee can be derived from the text of this sheet. You can always consult us for information.



Plantag Coatings Groep

Delta 32, 6825 MS Arnhem

T +31 (0) 26 388 21 02

F +31 (0) 26 364 41 51

Email: info@plantag.nl

Website: www.plantag.nl

application

Application method	Spray
Layers	1-3 layers
Yield per layer	130-170 gr/ m ²
Max. Yield	200 gr/ m ²
Optimal temp. working space	16-18 °C
Optimal humidity	60 %
Material temperature	16-20 °C
Cleaning Thinner	SO 602020
Pre-treatment of wood	P 120
Suitable on bleached wood	Does not applicable
UV resistance	Good
Optimal moisture content wood	7-10 %
Drying times	15 min. dust dry. 30 min. sprayable 2 hour sandable. 16 hour stackable. Forced drying will reduce the drying time.

Disposal

Treat waste from paints or oil as chemical waste, dispose of as chemical waste.

Package

Available in 5, 10 or 25 Kg cans.

Safety, Standards and durability

Complies with the following standards DIN 688611B, EN71 Part 3, DIN 53160, DIN 4102-B1

UN Code 1263, paint, 3, VG II, (D/E) , GGVS / ADR

Info: Safety data sheet.

